

PARS PET BG 840 N/S

Crystalline Polyethylene Terephthalate (PET)

Product Description

BG 840 is a crystalline, high molecular weight thermoplastic polymer made by continuous melt-phase polymerization process followed by solid-state polymerization.

Characteristics

BG 840 is specially formulated bottle grade PET that is characterized by high I.V., and low acetaldehyde. The high I.V. confers good mechanical properties; high burst strengths and reduced bottle distension after filling.

Typical Applications

BG840 is especially suitable for the production of bottles for carbonated drinks. The high I.V. gives the bottle the extra mechanical strength required in hot countries due to the high pressures from carbonation. It can also be used for bottles for noncarbonated (except water) and other packaging applications, e.g. edible oil & thermoformed packaging.

Specifications:

PROPERTIES	Unit	BG 840 N	BG 840 S	Test Method
Intrinsic Viscosity	DL/g	0.84 ± 0.02	0.84 ± 0.02	ISO 1628-5
DEG Content	Wt%	≤ 1.8	≤ 1.5	ASTM E2409-4
Color (CIE Lab)	(L*)	≥ 90	≥ 95	ASTM D6290-5
Color (CIE Lab)	(b*)	≤ 2	≤ 1	ASTM D6290-5
Carboxyl End Group	Meq/Kg	≤ 32	≤ 32	ASTM D7409-7
Melting Point	°C	249 ± 3	249 ± 3	ASTM D3418-3
Acetaldehyde	PPM	≤ 1	≤ 1	ASTM F2013-5
Water Content	Wt%	≤ 0.3	≤ 0.3	ASTM D6869-3

Note: 1) 'Water Content' determined before packing.

2) 'Color' determined after crystallization.

3) All presented parameters would be the average of lab result.

Processing Conditions

The PET (BG 840) has to be dried to moisture content below about 30-40 ppm. The drying conditions typically used are 180 °C for 5 hours; the dew point of the drying air should be at least -40 °C. Typically injection temperatures of 285 °C may be used to get clear preforms with acceptable acetaldehyde level for Colas and flavored drinks. **Food Regulation**

BG 840 is suitable for food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact STPC local representative for certificate.

Storage and Handling

PET resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry with relative humidity below 50% and temperatures preferably don't exceed 50 °C. STPC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PET within 6 months after delivery.

Contact Us

....